

LAMCORR Division of Laminations, Inc. HIGH PERFORMANCE CORROSION RESISTANT PLASTIC SHEET

LAM PVDF-K Sheet | KYNAR[®] 2850 and 740 resin

Standard Un-backed Sheet and Fabric-backed Sheet and Rolls

Lamcorr offers extruded Kynar® 2850 (flex) and homopolymer 740 PVDF resins as standard sheet form and in fabric-backed rolls and sheets. Like ECTFE, PVDF provides an effective solution for mid-range service temperatures. Copolymer sees more frequent use in applications that require flexibility and thermoforming. Homopolymer provides more structural integrity and permeation resistance. Both PVDF grades, though versatile in corrosion protection, do not lend themselves to strong alkaline environments.

Typical properties:

	PROPERTY	ASTM SPEC	UNIT	Homopolymer	Copolymer
	Specific Gravity	D 792	****	1.78	1.78
Environment	Water Absorption	D570	%	<0.03	<0.05
	Abrasion Resistance	Taber CS 17	mg/1000	7.5	7
	Oxygen Index	D2863	%	44	43
	Flammability	UL 94	****	VO	VO
		FM 4910	****	YES	YES
	Coefficient of Friction	C1894	Static	0.20	0.26
		C1894	Dynamic	0.14	0.19
lechanical	Tensile Strength (yield)	D1708, D638	psi	6,000	5,000
	Elongation (break)	D1708, D638	%	100	300
	Flexural Modulus	D790 @ 23 C	psi	195,000	170,000
	Notched Izod Impact	D256 @ 23 C	ft-lb/in.	3	5
2	Shore D Hardness	D2240	***	78	72
Thermal	Continuous Service	Maximum	°C	127	123
	Temperature		°F	261	253
	Melting Point	D3418	°C	170	222
		D3418	°F	338	434
	Vicat Softening Point	D1525	°C	****	****
		D1525	°F	****	****
			in/in/℉		
	Coefficient of Expansion	E831 TMA	(10 ^-5)	7.2	8.5
	Deflection Temp (66psi)	D648	°C	140	124
	(66psi)	D648	°F	284	255
	Deflection Temp (264psi)	D648	°C	118	****
	(264psi)	D648	°F	244	****
				X Y	X

* Continuous Service Temperature based upon "non-chemical Dry Usage".

- * Table data reflects ASTM based average typical vendor data.
- * Data meant as general guidelines only.
- * Specific applications require additional testing by the buyer.
- * All properties based on standard unbacked product tests only



ADVANTAGES

- Good Corrosive Resistance
- Average Heat Resistance
- Smooth Surface Characteristics
- Low Co-efficient of Friction

PROVEN APPLICATIONS

- Highly corrosive acid storage
- Semicon wet-bench (FM 4910)
- Tank & Reactor Vessels
- Pulp & Paper Production
- Mild Alkaline Systems

STANDARD SIZES

- Roll 48" x 600" (50')
- Sheets 48" x 96"
- Gauge .060, .090, .118, .157"

STANDARD COLORS

• Natural – industry standard

CUSTOM SIZES, COLORS

Contact Inside Sales

FABRIC BACKING

- LAM PVDF(F) polyester
- LAM PVDF(P) PAN

WELDING MATERIALS

- 1/8" & 5/32" Round Rod
- 5/8" Flat Cap Strip

Disclaimer: The information contained herein though believed to be true in nature is meant as general guidelines only. As such Laminations Incorporated makes NO EXPRESSED OR IMPLIED WARRANTIES with regard to specific end uses of these materials. Each purchaser is responsible for establishing and determining the specific material requirements for a given application. Any direct or consequential damages resulting from the improper use of these materials are strictly the responsibility of the buyer. Laminations Incorporated limits its liability to the replacement value of any defective products. Laminations Incorporated will not be responsible for or held liable for the improper use of our materials with regard to patent infringements, nor should any of our literature be construed as an offer of indemnity for patent infringement.

nomopolym

AM PVDF

copolyme

AM PVDF

PRODUCT PROFILE